

# A·R·C·HITECTURAL

## ROOF COATINGS

# ROOF REPAIR 909

## • PRODUCT DATA SHEET

### • DESCRIPTION

Roof Repair 909 is a water-based modified asphalt sealant. It sets by loss of water evaporation and when cured creates an impregnable vapor barrier. Roof Repair 909 is black in color. Roof Repair 909 allows for considerable movement of the surface upon which it is applied including expansion joints. It bonds to most construction materials and bridges silicone sealants. This product is odorless.

### • RECOMMENDED USES

Roof Repair 909 is formulated for use to repair broken seals at metal roof flashings on all types of roofing products. Primer is usually not required. Roof Repair 909 works great on EPDM seams as well as expansion joints. Roof Repair 909 may be used with polyester, fiberglass, cloth or yellow jacket inter-plyes and can be used on both below and above grade construction materials including asphalt and concrete composites. Roof Repair 909 cures into both a waterproof and vapor barrier sealant. Application needs to be at temperatures 40° F and greater with no rain within 4 hours.

### • BENEFITS

Waterborne Modified Asphalt Technology  
Fast-Set or Flashing Grade  
Non-Toxic & Non-Hazardous  
Rated Potable Water Containment

- *Avoid prolonged contact with skin. Do not take internally. Do not induce vomiting. Call a physician. Keep containers covered when not in use. Provide ventilation. Use product with disposable rubber gloves. This product can FREEZE and must be stored in temperatures above 40 degrees Fahrenheit.*

### • TECHNICAL DATA

RESIN TYPE	Asphalt modified with urethane/latex
COVERAGE:	8-12 gallons per 100 square feet
COLOR:	Black
PERMEABILITY:	0.0024 Perms ASTM E-96 Vapor Barrier
SOLIDS:	Weight 72% +/- 1% ASTM D-1353
MILS:	80 to 140 mm
WEIGHT:	8.5 lbs. per gallon +/- 2%
VISCOSITY:	3,000 to 4,000 cps. (Can Be Thickened)
TENSILE:	58 psi @ 75 F ASTM D-412 2,556 lbs/ft <sup>2</sup> with fabric
ELONGATION:	1332% @ 75 F ASTM D-412
STORAGE:	12 months unopened between 40-100° F
DRY TIME:	1-4 hour at 75 F @ 60 wet mils Force-Set available with catalyst
FULL CURE:	12 - 24 hours @ 50% humidity at 78 F air movement, and temperature
CLEAN-UP:	Wet-soap and water; Dry-citrus cleaner
ADHESION:	Pass (concrete, asphalt) ASTM D-413
TEAR:	Strength at 69 lbs./inch ASTM D-624
FIRE RATING:	Class "A" ASTM-E-108 (w/ FR-Catalyst)
FLASH:	None ASTM D-1310 STORE FROM FREEZE (40° F)

### DISTRIBUTED BY:

There is no warranty given, expressed or implied, through the values or statements made here, nor are there any assertions that the product purchased has been individually tested to conform to these standards. Testing is performed on a random basis by our in house and independent third party labs in order to obtain approval and/or classification. Acceptance, purchase and selection of these products are the sole responsibility of the buyer, buyer's agent, or the buyer's customer. ARC assumes no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of the product. NO OTHER GUARANTY OR WARRANTY OF ANY KIND IS MADE BY ROOF COATINGS, INC. OR ITS SUBSIDIARIES, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.